

Scotch® Filament Tape 8915



Technical Data

April, 2003

Product Description Scotch® Filament Tape 8915 is a high-performance transparent tape reinforced with continuous high strength glass filaments which is designed to hold appliance parts together during manufacture and shipping. The heavy 3M™ Scotchpro™ film backing provides proper stiffness and excellent abrasion, moisture, and scuff resistance. The pressure sensitive adhesive is specifically formulated to provide high adhesion, clean removal, and stain resistance on most finishes.

Construction	Backing	Adhesive	Reinforcement	Backing Color
	3M™ Scotchpro™ film	Pressure sensitive synthetic rubber resin	Glass yarn	Clear

Typical Physical Properties **Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.**

		ASTM Test Method
Adhesion to Steel:	60 oz./in. width (65 N/100 mm width)	D-3330
Tensile Strength:	170 lbs./in. width (2980 N/100 mm width)	D-3759
Elongation at Break:	3%	D-3759
Total Thickness:	6 mil (0.15 mm)	D-3652

Available Sizes

Standard Widths:	.47 in. (12 mm), .71 in. (18 mm), .94 in. (24 mm), 1.4 in. (36 mm), 1.7 in. (42 mm), 2.4 in. (60 mm) and 2.8 in. (72 mm)
Core Size (ID):	3 in. (76.2 mm)
Lengths:	60 yds. (55 m)

Storage Conditions Store behind present stock. Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40-50% relative humidity are recommended. Rotate your stock.

Scotch® Filament Tape

8915

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/packaging. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Important Notice

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's application.

Limitation of Remedies and Liability

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.

ISO 9002

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

3M

**Industrial Business
Industrial Adhesives and Tapes Division**

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000



*Recycled Paper
40% pre-consumer
10% post-consumer*

Printed in U.S.A.
©3M 2003 70-0710-0273-0 (4/03)